

Northumbria Research Link

Citation: Zoppi, Guillaume, Beattie, Neil, Major, Jonathan, Miles, Robert and Forbes, Ian (2011) Electrical, morphological and structural properties of RF magnetron sputtered Mo thin films for application in thin film photovoltaic solar cells. *Journal of Materials Science*, 46 (14). pp. 4913-4921. ISSN 0022-2461

Published by: Springer

URL: <http://dx.doi.org/10.1007/s10853-011-5404-0> <<http://dx.doi.org/10.1007/s10853-011-5404-0>>

This version was downloaded from Northumbria Research Link:
<https://nrl.northumbria.ac.uk/id/eprint/2234/>

Northumbria University has developed Northumbria Research Link (NRL) to enable users to access the University's research output. Copyright © and moral rights for items on NRL are retained by the individual author(s) and/or other copyright owners. Single copies of full items can be reproduced, displayed or performed, and given to third parties in any format or medium for personal research or study, educational, or not-for-profit purposes without prior permission or charge, provided the authors, title and full bibliographic details are given, as well as a hyperlink and/or URL to the original metadata page. The content must not be changed in any way. Full items must not be sold commercially in any format or medium without formal permission of the copyright holder. The full policy is available online: <http://nrl.northumbria.ac.uk/policies.html>

This document may differ from the final, published version of the research and has been made available online in accordance with publisher policies. To read and/or cite from the published version of the research, please visit the publisher's website (a subscription may be required.)

Electrical, Morphological and Structural Properties of RF Magnetron Sputtered Mo Thin Films for Application in Thin Film Photovoltaic Solar Cells

Guillaume Zoppi^{1*}, Neil S. Beattie¹, Jonathan D. Major², Robert W. Miles and Ian Forbes¹

¹Northumbria Photovoltaics Applications Centre, Northumbria University, Ellison Building, Newcastle upon Tyne, NE1 8ST, UK

²Physics Department, Durham University, South Road, Durham, DH1 3LE, UK

*Corresponding author: guillaume.zoppi@northumbria.ac.uk, tel: +44 (0)191 243 7013

ABSTRACT

Molybdenum (Mo) thin films were deposited using radio frequency (RF) magnetron sputtering, for application as a metal back contact material in “substrate configuration” thin film solar cells. The variations of the electrical, morphological, and structural properties of the deposited films with sputtering pressure, sputtering power and post-deposition annealing were determined. The electrical conductivity of the Mo films was found to increase with decreasing sputtering pressure and increasing sputtering power. X-ray diffraction data showed that all the films had a (110) preferred orientation that became less pronounced at higher sputtering power while being relatively insensitive to process pressure. The lattice stress within the films changed from tensile to compressive with increasing sputtering power and the tensile stress increased with increasing sputtering pressure. The surface morphology of the films changed from pyramids to cigar-shaped grains for a sputtering power between

100 and 200 W, remaining largely unchanged at higher power. These grains were also observed to decrease in size with increasing sputtering pressure. Annealing the films was found to affect the resistivity and stress of the films. The resistivity increased due to the presence of residual oxygen and the stress changed from tensile to compressive. The annealing step was not found to affect the crystallisation and grain growth of the Mo films.

INTRODUCTION

Molybdenum (Mo) is the most commonly used metal for back contacts in chalcopyrite (CuInGaSe₂, CIS) based thin film solar cells [1]. Other metals can be used [2, 3], however Mo is the main choice for this application because the Mo layer offers high stability to processing temperature (up to 600°C) and good adherence to the substrate (which is usually glass) whilst providing a high conductivity and low resistance contact to the CIS absorber layer. Common deposition methods include electron beam evaporation [4, 5] or sputtering, using either a direct current (DC) [3, 6-9] or radio frequency (RF) [10-12] technique. Sputtering, and in particular DC sputtering, has been the method of choice for studying the properties of Mo films since the pioneering work of Scofield [3]. It is also the method which has resulted in the highest solar efficiency [1]. There are fewer reports on RF sputtering and only recently Khatri *et al.* have performed a limited study of how the Mo properties vary with the deposition parameters; however the resistivity and stress values achieved were higher than desirable for application in thin film solar cells [10]. As with DC sputtering, RF sputtering parameters such as deposition rate and argon pressure affects lattice stress, crystallographic orientation, electrical and morphological properties; however these are also correlated to the deposition system itself. In this work, an in-depth systematic study of how the physical properties of Mo films formed by RF sputtering has been carried out, with the

aim of determining which growth parameters control the film properties, to determine the conditions for producing low resistivity, low stress Mo films, for application in photovoltaic solar cell device structures.

EXPERIMENTAL

Mo thin films were deposited by magnetron RF sputtering onto commercially available soda-lime glass substrates. The substrates of dimensions 76x26x1 mm³ were mechanically cleaned in diluted Decon90 solution, rinsed in high purity water and then blown dried in a flow of nitrogen. The depositions took place in a 3x6'' target magnetron sputter down Nordiko2000 system setup for sequential sputtering using high purity (99.95%) Mo target and argon (99.998% pure) as the sputtering gas. The rotating substrate table was equipped with 4 substrate holders each capable of holding 5 substrates. The base pressure of the vacuum chamber was 5×10^{-7} Torr. The sputtering power was varied from 100 to 900 W and the working pressure from 2 to 22 mTorr. The deposition time was adjusted to yield a film thickness of ~840 nm.

The samples were subsequently annealed at 530°C for 45 min in a tube furnace evacuated to a primary vacuum level (5×10^{-3} mTorr). The samples were placed in a graphite box to mimic the conditions of selenisation/sulfurisation processes used in the absorber fabrication. Prior to annealing, the tube was backfilled with either high purity argon or forming gas (a 10% mixture H₂ in N₂ gas) to a pressure of 6 and 10 mbar, respectively. The heating and cooling rate were 25°C/min and 2.5°C/min, respectively. These conditions have previously been used to produce the Mo used to successfully produce thin film solar devices [13, 14].

The structural properties of the deposited layers were analysed using X-ray diffractometry (XRD) using a Siemens D-5000 diffractometer. Scanning electron microscopy SEM (carried out using a Hitachi SU-70 SEM) and atomic force microscopy (AFM) (carried out using a Veeco Multimode AFM) were used to assess the morphological properties. The resistivity was determined using a 4-point probe setup (using a Jandel Engineering LTD 4-probe and Keithley 2602 sourcemeter).

RESULTS AND DISCUSSION

1-Power density effect

The power applied to the target was varied between 100 and 900 W, while the chamber pressure was maintained at a pressure of 5 mTorr. The deposition time was adjusted between 43 and 580 min to maintain the thickness at 840 nm \pm 20 nm. All films showed good adhesion to the glass substrate, with no delamination observed during further processing or during the tape test [8]. A summary of the electrical and crystallographic properties is shown in Table 1. It can be seen (Table 1 and Fig 1) that, as expected, the growth rate increases linearly with increasing power. Fig 1 also shows the evolution of the sheet resistance as a function of the sputtering power. For equivalent thickness, the sheet resistance (R_s) of the Mo film decreases sharply when the power is ramped up from 100 to 200 W before decreasing with a much slower rate for higher sputtering powers. Sheet resistances of less than 0.5 Ω/\square are achieved for sputtering powers greater than 300 W; these are low enough for back contact applications in thin film solar cells. Upon annealing the sheet resistance of the films is increased by a factor of ~ 2 (Fig 1). This is due to the formation of a molybdenum oxide layer at the surface of the Mo, due to the Mo at the surface reacting with residual oxygen present in

the primary vacuum of the furnace. This would not occur when making solar cells devices because of the presence of additional layers on top of the Mo film during this annealing step.

XRD was used to analyse the crystallographic properties of the deposited films. The inset of Fig 2 shows a full scan for a typical film. The reflections corresponding to the (110), (211) and (220) planes are detected for diffraction angles of 40.5° , 73.7° and 87.6° respectively. A fourth reflection at 36.5° is also present but is due to spectral contamination from the beta filter in the XRD setup. Fig 2 shows in detail the (110) reflection, and indicates that the (110) peak intensity decreases with increasing power. More importantly, the peak position shifts as the sputtering power is varied which reflects a change in lattice parameter of the deposit and hence stress, in the films. The detailed position and characteristics of each peak were determined by fitting the data using a Pseudo-Voigt function [15]. From the (110) peak position, the lattice parameter a of the Mo cubic structure was calculated and the relative variation of a compared to the Mo reference lattice parameter $a_0 = 3.1472 \text{ \AA}$ [16] yields the extent of stress in the crystal lattice. Negative or positive values can be deduced indicating compressive or tensile stress, respectively. The full width at half maximum (FWHM) of the (110) peak may be used to determine the crystallite size of the structure, via the Scherrer formula [10], as long as the size remains small ($<200 \text{ nm}$). The variation of FWHM, crystallite size and stress values are shown in Table 1, Fig 3 and 4. The FWHM of the (110) peak is broadest for the film deposited at 100 W, but it remains relatively invariant for larger powers. The crystallite size varies between 13 and 45 nm but these variations are small between 200 and 900 W. Some fluctuations are observed, but the extent is much less than reported elsewhere [10]. We note that the films exhibit tensile stress at low power and this is gradually reduced to become unstressed, or just compressive, for powers greater than 500 W (Fig. 4). It has been suggested that voids, crystallographic impurities, oxygen or argon

impurities could be responsible for the stress in the sputtered Mo films. It is argued that these effects are related to the frequency of gas phase collisions in the sputtering system which alters the kinetic energy of both Ar and Mo atoms [3, 10, 17]. At high deposition powers the energy of the sputtering gas is high resulting in higher deposition rate and the sputtered Mo atoms have high kinetic energy yielding films with less voids and a lower inclusion of impurities (*i.e.* Ar or O). This yields a higher conductivity for a higher power and a reduction of tensile stress. However as the stress is further reduced for very high power it becomes compressive as the compressive atom peening exceeds the intra-grain tensile forces. This trend is broken when the power is reduced to 100 W and this is due in part to the film becoming more amorphous; however the reason for this is not fully known. Overall the stress levels measured are very small, at least an order of magnitude smaller than those reported by Khatri [10].

The effects of post growth heat treatment, using an annealing temperature of 530°C and annealing time of 45 min in 6 mbar Ar atmosphere, on the FWHM and stress values are shown in Fig 3 and 4. No substantial change is observed in the FWHM values (fig 3) indicating no grain evolution under those annealing conditions. The effect on the lattice structure is more pronounced (Fig 4). Upon heating compressive stress is introduced in all films. The recrystallization temperature of Mo is > 900°C and therefore very little change in structural and electrical properties would be expected at temperatures below 650°C [18]. However, the soda-lime glass substrate has an annealing point and strain point of 546°C and 511°C, respectively, according to various manufacturers. These temperatures are close to the experimental heat treatment temperature of 530°C used in this work, which when associated with the thermal expansion of the glass, we believe this is the reason of the variations of stress in the Mo films following annealing. At 530°C the glass starts to soften allowing the Mo film to relax. The thermal expansion of the substrate at this temperature is as much as

0.4% of its length therefore during the slow cool down of the heat treatment the contraction of the glass yields compressive stress in the Mo film.

In order to study the effects of the growth conditions on texture and preferred orientation of the Mo film samples, the texture coefficients C_{hkl} [19] were studied where

$$C_{hkl} = \frac{\frac{I_{hkl}}{I_{r,hkl}}}{\frac{1}{n} \sum_n \frac{I_{hkl}}{I_{r,hkl}}} \quad (1)$$

and n is the number of reflections, I_{hkl} the intensity of the hkl reflection and $I_{r,hkl}$ the intensity of the hkl reflection for a completely random sample. Hence C_{hkl} gives a measure of the enhancement of the hkl reflection in comparison to a completely randomly oriented sample. The preferred orientation of each film, as a whole, was analysed from the standard deviation σ of all C_{hkl} values as compared with randomly oriented samples as:

$$\sigma = \sqrt{\sum \frac{1}{n} (C_{hkl} - 1)^2} \quad (2)$$

σ values are used to compare the degree of orientation between different samples, so that lower σ values indicate more randomly oriented samples. For a completely randomised sample the C_{hkl} coefficients would be 1 and the preferred orientation 0 while for a fully aligned sample the C_{hkl} would be 3 for that particular direction and 0 for the others and the degree of preferred orientation 1.4. The variations of texture coefficients are shown in Table 2.

The data indicates a strong preferred orientation in the (110) direction for all samples. However as the power is increased a slight loss of this preferred orientation is observed via a

decrease in the values of C_{110} and σ . Meanwhile C_{211} and C_{220} values increase and decrease, respectively, indicating a slight shift of orientation from (110) into the (211) direction. The sample deposited at 100 W is anomalous in this respect as the (110) peak is the smallest and broadest for any of the samples in this set, whilst the (220) peak is hardly visible, indicating very small grained structure with a stronger orientation in the (211) direction. We believe this indicates why the electrical and lattice properties of this 100 W film are significantly different from the other deposition powers used. Following annealing at 530°C for 45 min no change is observed in the crystallite orientation and the films remains strongly (110) oriented.

The surface topology was observed by both SEM and AFM. Fig 5 (a-e) shows the AFM micrographs for films deposited between 100 and 900 W. At 100 W the films show grains with a triangular shape. Between 200 and 600 W the grains have a cigar-shape and are well orientated. For sputtering power greater than 600 W, the grains do not seem to be as well ordered with variations in size starting to appear. Overall however, very little change in grain sizes is observed between 200-900 W and this confirms the XRD data. The films' average roughness is between 6 and 10 nm for all films. Fig 5 (f) shows a SEM cross section view of a film deposited at 300 W. The structure is columnar showing narrow grains extending the full thickness of the films which is typical of a sputtered Mo thin film.

2-Effect of sputtering pressure

For this study the power and deposition time were fixed at 300 W and 120 min, respectively. The chamber pressure was altered by keeping the gas flow constant and varying the pumping speed. The properties for the as-deposited films are summarized in Table 3. The growth rate

is increased nonlinearly with pressure (Fig 6), giving a variation of 60 nm in thickness between extreme deposition conditions for a given deposition time. Under these conditions the variations in thickness have no noticeable effect on the film properties. The variations of sheet resistance versus chamber pressure are also shown in Fig 6, with higher sheet resistance being measured for deposited at higher pressure. This trend is in good agreement with other published data [3, 10].

The electrical properties of the films following post-deposition annealing (530°C, 45 min) in argon or forming gas (H_2N_2) ambient are also shown in Fig 6. Following either of the heat treatments the sheet resistance values doubled for all but the lowest pressure sample. There is therefore no influence of the annealing gas ambient on the electrical properties of the films. As described in the previous section this is due to the formation of Mo oxides at the surface during the annealing process.

The XRD spectrum around the (110) peak is shown in Fig 7. The (110) peak intensity increases when the pressure is increased from 2 to 8 mTorr, but for higher pressure values the peak becomes smaller and broader. This reflects an increase in crystallite size when the pressure is increased from 2 to 8 mTorr; however beyond ~10 mTorr, this effect is lost and the structural quality degrades. The stress and FWHM values calculated from the (110) XRD data are shown in Fig 8 and 9, respectively. Overall the stress measured is tensile in all cases, less than 0.1% compared to an unstressed film for as-deposited films and decreases for lower deposition pressure. Broader (110) peaks are observed for films deposited at higher pressure (Fig 9), meaning that the crystallite size of grains orientated in the (110) direction is decreased as the deposition pressure is increased (see also Table 3). Similarly to the previous section, both stress and sheet resistance data can be linked together with the sputtering pressure and the frequency of gas-phase collisions. When reducing the sputtering pressure, the frequency of gas-phase collisions is also reduced and this in turn increases the kinetic

energy of the sputtered Mo atoms and neutral Ar atoms from the plasma. It is suggested that the resulting Mo film structure is denser with less intra-grain voids porous grains [3]. This yields a more conductive film and also a less stressed film as observed in Fig 6 and 8. For pressures greater than 10 mTorr the concentrations of defects is such that the films show an apparent reduced crystalline quality (Fig 7 and 9) as indicated by the broader peaks. Upon annealing the stress becomes compressive in all cases except at the highest pressure. The trend as function of gas ambient remains similar to that of the as-grown films however, it can be observed that the absolute change in stress after annealing is less for films deposited at higher pressure. Following the above discussion the stress can be associated with the sputtering pressure such that lower deposition pressures yield more densely packed columnar grains towards compressive stress whereas higher pressure tends to form a more porous structure under tensile stress [20, 21]. Therefore the porous nature of the films deposited at higher pressure allows more “flexibility” in the films and more resilience to the annealing process. No change in FWHM values are observed after annealing, indicating that the Mo films are not subject to any grain growth or recrystallisation during this step. This confirms the previous observation.

The variations of texture coefficients and degree of preferred orientation as a function of sputtering pressure and annealing atmosphere are shown in Table 4. The degree of preferred orientation is greatest for film deposited at pressures of 5.5 and 8 mTorr, however the change in texturing is marginal for the other pressure values.

The surface topology and morphology, i.e. grains size and shape of the deposited films were studied in detail by SEM and AFM, with micrographs being shown in Fig 10. It was found that not only the size but the shape is affected by the deposition conditions. At 2 mTorr the

grains are the largest and are well ordered. At 5 mTorr some grains present sharp triangular tails, while at 8 mTorr the films become smoother and the grains seem to break down into smaller ones. At 12 mTorr all the grains have pyramidal shapes, whereas at 22 mTorr the structure is the most compact with small bean shape grains.

The AFM images were analysed using the Gwyddion software package to determine the grain size distribution at each deposition pressure. These are shown in Fig 11 where each distribution has been fitted with a Gaussian to obtain an average which is shown in Fig 12. From Figs 11 and 12 it is apparent that the average equivalent grain radius decreases from approximately 29 nm to 20 nm as the pressure increases from 2 mTorr to 22 mTorr. This is in reasonable agreement with grain size data obtained from XRD (also shown in Fig 12). Furthermore, it is also apparent from Fig. 11 that at 22 mTorr the standard deviation of the grain size distribution is smaller than at lower pressures, indicating a greater degree of similarity between grains. The average surface roughness R_a , was also obtained from the AFM data and is shown in Fig. 12. A general trend of increasing surface roughness with pressure was observed between 2 mTorr and 12 mTorr. A further increase of 10 mTorr resulted in a decrease in surface roughness to $R_a \approx 6$ nm at 22 mTorr. This is consistent with the observed decrease in standard deviation of grain size distribution at this pressure and suggests a different regime of grain formation. This change may be related to increased collisions of Mo atoms with sputtering ions at higher pressure which reduces their kinetic energy and results in more oblique impact angles of incident Mo atoms on the substrate [3].

CONCLUSIONS

The electrical, morphological and crystallographic properties of Mo thin films deposited by RF magnetron sputtering have been investigated as a function of sputtering power and

pressure. All the films deposited in this study had good adhesion to the substrate regardless of the deposition parameters investigated. The electrical conductivity of the Mo films has been measured to increase with decreasing sputtering pressure and increasing sputtering power. All the films showed a (110) preferred orientation that became less pronounced at higher sputtering power while being relatively insensitive to the process pressure. The lattice stress within the films changed from tensile to compressive with increasing power. The tensile stress increased with increasing sputtering pressure. The grain size and shape remained unchanged for films deposited at sputtering power between 200 and 900 W, whereas grain size decreases with increasing sputtering pressure. Post annealing of the Mo films in argon or forming gas increased the resistivity of the films due to the formation of an oxide layer at the surface and the lattice stress changed from tensile to compressive. From this experiment optimum Mo films properties for thin film solar cell applications are achieved for sputtering power between 300 and 600 W and sputtering pressure around 5 mTorr.

ACKNOWLEDGEMENTS

The authors acknowledge support of the UK Engineering and Physical Sciences Research Council SUPERGEN Initiative for the program 'PV-21'.

REFERENCES

1. Repins, I., M.A. Contreras, B. Egaas, C. DeHart, J. Scharf, C.L. Perkins, B. To, and R. Noufi, *19.9%-efficient ZnO/CdS/CuInGaSe₂ solar cell with 81.2% fill factor*. Progress in Photovoltaics: Research and Applications, 2008. **16**(3): p. 235-239.
2. Orgassa, K., H.W. Schock, and J.H. Werner, *Alternative back contact materials for thin film Cu(In,Ga)Se₂ solar cells*. Thin Solid Films, 2003. **431-432**: p. 387-391.

3. Scofield, J.H., A. Duda, D. Albin, B.L. Ballard, and P.K. Predecki, *Sputtered molybdenum bilayer back contact for copper indium diselenide-based polycrystalline thin-film solar cells*. Thin Solid Films, 1995. **260**(1): p. 26-31.
4. Guillen, C. and J. Herrero, *Low-resistivity Mo thin films prepared by evaporation onto 30 cm x 30 cm glass substrates*. Journal of Materials Processing Technology, 2003. **143-144**: p. 144-147.
5. Hoffman, R.A., J.C. Lin, and J.P. Chambers, *The effect of ion bombardment on the microstructure and properties of molybdenum films*. Thin Solid Films, 1991. **206**(1-2): p. 230-235.
6. Gordillo, G., M. Grizalez, and L.C. Hernandez, *Structural and electrical properties of DC sputtered molybdenum films*. Solar Energy Materials and Solar Cells, 1998. **51**(3-4): p. 327-337.
7. Shen, Y.G., *Effect of deposition conditions on mechanical stresses and microstructure of sputter-deposited molybdenum and reactively sputter-deposited molybdenum nitride films*. Materials Science and Engineering A, 2003. **359**(1-2): p. 158-167.
8. Kadam, A.A., N.G. Dhere, P. Holloway, and E. Law, *Study of molybdenum back contact layer to achieve adherent and efficient CIGS2 absorber thin-film solar cells*. Journal of Vacuum Science & Technology A-Vacuum Surfaces and Films, 2005. **23**(4): p. 1197-1201.
9. Alleman, J.L., H. Althani, R. Noufi, H. Moutinho, M. Al-Jassim, and F. Hasoon. *Dependence of the characteristics of Mo films on sputter conditions*. in *NCPV Program Review Meeting*. 2000. Denver, Colorado, p. 239-240.
10. Khatri, H. and S. Marsillac, *The effect of deposition parameters on radiofrequency sputtered molybdenum thin films*. Journal of Physics: Condensed Matter, 2008. **20**(5): p. 055206.
11. Assmann, L., J.C. Bernede, A. Drici, C. Amory, E. Halgand, and M. Morsli, *Study of the Mo thin films and Mo/CIGS interface properties*. Applied Surface Science, 2005. **246**(1-3): p. 159-166.
12. Martinez, M.A. and C. Guillen, *Effect of r.f.-sputtered Mo substrate on the microstructure of electrodeposited CuInSe2 thin films*. Surface and Coatings Technology, 1998. **110**(1-2): p. 62-67.
13. Dale, P.J., A.P. Samantilleke, G. Zoppi, I. Forbes, and L.M. Peter, *Characterization of CuInSe2 material and devices: comparison of thermal and electrochemically prepared absorber layers*. Journal of Physics D: Applied Physics, 2008. **41**(8): p. 085105.
14. Zoppi, G., I. Forbes, R.W. Miles, P.J. Dale, J.J. Scragg, and L.M. Peter, *Cu2ZnSnSe4 thin film solar cells produced by selenisation of magnetron sputtered precursors*. Progress in Photovoltaics: Research and Applications, 2009. **17**(5): p. 315-319.
15. Vergara, L., J. Olivares, E. Iborra, M. Clement, A. Sanz-Hervás, and J. Sangrador, *Effect of rapid thermal annealing on the crystal quality and the piezoelectric response of polycrystalline AlN films*. Thin Solid Films, 2006. **515**(4): p. 1814-1818.
16. Robbmond, A. and B.J. Thijsse, *Ion-beam assisted deposition of thin molybdenum films studied by molecular dynamics simulation*. Nuclear Instruments and Methods in Physics Research Section B: Beam Interactions with Materials and Atoms, 1997. **127-128**: p. 273-277.
17. Malhotra, S.G., Z.U. Rek, S.M. Yalisove, and J.C. Bilello, *Strain gradients and normal stresses in textured Mo thin films*. Journal of Vacuum Science & Technology A: Vacuum, Surfaces, and Films, 1997. **15**(2): p. 345-352.
18. Schmid, U. and H. Seidel, *Effect of substrate properties and thermal annealing on the resistivity of molybdenum thin films*. Thin Solid Films, 2005. **489**(1-2): p. 310-319.

19. Moutinho, H., M. Al-Jassim, D.H. Levi, P.C. Dippo, and L.L. Kazmerski, *Effects of CdCl₂ treatment on the recrystallization and electro-optical properties of CdTe thin films*. Journal of Vacuum Science and Technology, 1998. **A 16**(3): p. 1251-1257.
20. Probst, V., J. Rimmasch, W. Riedl, W. Stetter, J. Holz, H. Harms, F. Karg, and H.W. Schock. *The impact of controlled sodium incorporation on rapid thermal processed Cu(InGa)Se₂-thin films and devices*. in *Proceedings of 1994 IEEE 1st World Conference on Photovoltaic Energy Conversion*. 1994, p. 144-147.
21. Vink, T.J., M.A.J. Somers, J.L.C. Daams, and A.G. Dirks, *Stress, strain, and microstructure of sputter-deposited Mo thin films*. Journal of Applied Physics, 1991. **70**(8): p. 4301-4308.

List of Tables

Table 1: Properties of as-deposited Mo thin films as a function of sputtering power.

Table 2: Texture coefficients and degree for preferred orientation for as-deposited and argon annealed Mo films.

Table 3: Properties of as-deposited Mo thin films as a function of sputtering pressure.

Table 4: Texture coefficients and degree for preferred orientation for as-deposited and annealed Mo films as a function of sputtering pressure.

List of figures

Fig 1: Growth rate as a function of sputtering power (●); sheet resistance as a function of sputtering power (■) and sheet resistance as a function of sputtering power after annealing at 530°C for 45 min (□).

Fig 2: (110) XRD patterns of Mo films deposited as a function of sputtering power. The inset shows a full scan.

Fig 3: (110) peak FWHM as a function of sputtering power for as deposited (■) and argon annealed films (●)

Fig 4: Lattice stress of Mo films as a function of sputtering power for as deposited (■) and argon annealed films (□).

Fig 5: AFM micrographs for films deposited at (a) 100 W, (b) 200 W, (c) 400 W, (d) 600 W and (e) 900 W. (f) A cross sectional SEM image of sample deposited at 300 W.

Fig 6: Growth rate versus sputtering pressure (\diamond) and sheet resistance versus sputtering pressure for as-deposited layers (\blacksquare), argon annealed (\bullet) and forming gas annealed (\blacktriangle) Mo thin films.

Fig 7: XRD patterns of Mo films deposited as a function of sputtering pressure.

Fig 8: Evolution of the lattice stress as a function of deposition pressure for as deposited films (\blacksquare), argon annealed (\bullet) and H_2N_2 annealed (\blacktriangle) films.

Fig 9: Evolution of the (110) FWHM as a function of deposition pressure for as deposited film (\blacksquare), argon annealed (\bullet) and H_2N_2 annealed (\blacktriangle) films.

Fig 10: 3D AFM (left) and SEM (right) micrographs of Mo thin films as a function of deposition pressure.

Fig 11: Grain size distribution as a function sputtering pressure. The data was fitted using a Gaussian distribution.

Fig 12: Roughness (\circ) and grain size measurement from AFM images analysis (\blacksquare) and XRD measurements (\blacktriangle) as a function of sputtering pressure.

Table 1: Properties of as-deposited Mo thin films as a function of sputtering power

Power (W)	Growth Rate (nm/min)	Sheet resistance (Ω/\square)	Resistivity ($\mu\Omega\cdot\text{cm}$)	(110) FWHM ($^\circ$)	Stress (%)	Grain Size (XRD) (nm)
100	1.6	3.52	310	0.494	-0.789	13
200	3.3	0.70	57.1	0.244	0.022	39
300	7.1	0.48	40.4	0.314	0.015	30
400	8.0	0.42	36.2	0.260	0.008	36
500	10.7	0.42	35.4	0.284	-0.004	33
600	13.0	0.45	36.7	0.194	-0.001	45
900	18.6	0.30	23.9	0.222	-0.051	42

Table 2 Texture coefficients and degree for preferred orientation for as-deposited and argon annealed Mo films

Power (W)	As-deposited				Argon Annealed			
	C ₁₁₀	C ₂₁₁	C ₂₂₀	σ	C ₁₁₀	C ₂₁₁	C ₂₂₀	σ
100	2.59	0.41	0.00	1.14	2.56	0.44	0.00	1.11
200	2.44	0.01	0.54	1.04	2.42	0.02	0.56	1.03
300	2.44	0.03	0.53	1.04	2.41	0.04	0.55	1.02
400	2.43	0.03	0.54	1.03	2.31	0.16	0.53	0.94
500	2.36	0.11	0.53	0.98	2.38	0.10	0.53	0.99
600	2.37	0.14	0.49	0.98	2.42	0.04	0.54	1.03
900	2.30	0.18	0.52	0.93	2.28	0.20	0.52	0.92

Table 3: *Properties of as-deposited Mo thin films as a function of sputtering pressure*

Pressure (mTorr)	Growth Rate (nm/min)	Sheet resistance (Ω/\square)	Resistivity ($\mu\Omega\cdot\text{cm}$)	(110) FWHM ($^\circ$)	Stress (%)	Grain Size (XRD) (nm)
2.3	6.83	0.260	21.3	0.248	0.046	37.9
5.5	7.00	0.480	40.3	0.314	0.015	30.0
8	7.17	0.616	53.0	0.301	0.081	31.3
12	7.25	0.920	80.0	0.605	0.055	15.5
22	7.33	2.244	197.5	0.720	0.096	13.1

Table 4 Texture coefficients and degree for preferred orientation for as-deposited and annealed Mo films as a function of sputtering pressure

Pressure (mTorr)	As-deposited				Argon Annealed				H ₂ N ₂ Annealed			
	C ₁₁₀	C ₂₁₁	C ₂₂₀	σ	C ₁₁₀	C ₂₁₁	C ₂₂₀	σ	C ₁₁₀	C ₂₁₁	C ₂₂₀	σ
2.3	2.38	0.09	0.53	0.99	2.37	0.10	0.53	0.98	2.42	0.02	0.56	1.03
5.5	2.44	0.03	0.53	1.04	2.41	0.04	0.55	1.02	2.41	0.04	0.55	1.02
8	2.44	0.01	0.55	1.04	2.42	0.01	0.57	1.03	2.43	0.01	0.57	1.03
12	2.35	0.02	0.64	0.99	2.34	0.01	0.64	0.98	2.37	0.01	0.61	1.00
22	2.37	0.04	0.60	0.99	2.37	0.04	0.59	0.99	2.39	0.04	0.57	1.00























